

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188	
<small>Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing this collection of information. Send comment regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.</small>				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE 4/20/99		3. REPORT TYPE AND DATES COVERED Interim Report, 6/1/98 - 12/31/98
4. TITLE AND SUBTITLE New Microlayer and Nanolayer Polymer Composites			5. FUNDING NUMBERS DAAG55-98-1-0311	
6. AUTHOR(S) E. Baer and A. Hiltner				
7. PERFORMING ORGANIZATION NAMES(S) AND ADDRESS(ES) Case Western Reserve University 10900 Euclid Avenue Cleveland, Ohio 44106-7202			8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army Research Office P.O. Box 12211 Research Triangle Park, NC 27709-2211				
11. SUPPLEMENTARY NOTES The views, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy or decision, unless so designated by other documentation.				
12a. DISTRIBUTION / AVAILABILITY STATEMENT  Approved for public release; distribution unlimited.			12 b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words)  During the period, new types of micro- and nano- layered polymeric composite systems were created with specific property combinations. Various materials systems with two and three components were produced for the first time. These had novel characteristics due to structure control as a function of scale and inter-layer adhesion.  Highlights include: (1) Development of clear nano-layered composites with improved ballistic performance characteristics;  (2) Creation of conducting micro-layered composites by controlled interdiffusion;  (3) Microlayered structures with highly anisotropic conductivity				
14. SUBJECT TERMS			15. NUMBER OF PAGES	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OR REPORT UNCLASSIFIED			18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	
19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED			20. LIMITATION OF ABSTRACT UL	

20011102 012

1. Manuscripts Submitted and Published

Mechanical Behavior of Polymer Microlayers, by J. Kerns,  
A. Hsieh, A. Hiltner and E. Baer, Macromol. Symp. (in press).

Relationships of Hierarchical Structure to Mechanical Properties,  
by D. Jarus, A. Hiltner and E. Baer, Macromol. Symp. (in press)

Solid State Structure and Melting Behavior of Interdiffused  
Polyethylene in Microlayers, by T. Schuman, S. Nazarenko,  
E.V. Stepanov, S.N. Magonov, A. Hiltner and E. Baer,  
Polymer (in press)

Creating Layers of Concentrated Inorganic Particles by  
Interdiffusion of Polyethylene in Microlayers, by S. Nazarenko,  
M. Dennison, T. Schuman, E.V. Stepanov, A. Hiltner and E. Baer,  
J. Appl. Polym. Sci. (in press)

Microlayer Structures with Anisotropic Conductivity, by  
S. Nazarenko, A. Hiltner and E. Baer, J. Mater. Sci., 33, 1-10  
(1998).

2. Scientific Personnel

Faculty:

E. Baer, professor  
A. Hiltner, professor  
S. Nazarenko, assistant professor

Research Staff and Graduate Students

E. Stepanov, Senior Research Associate  
T. Schuman, Ph.D. candidate  
M. Parsons, Ph.D. candidate  
D. Jarus, PhD. candidate  
J. Kerns M.S. candidate  
M. Dennison, B.S. candidate

3. Inventions

None

#### 4. Scientific Progress and Accomplishments

Transparent nanolayered composites with more than 4,000 layers have been created of both polycarbonate/styrene acrylonitrile copolymers and polycarbonate/polymethylmethacrylate. A composition of 80% polycarbonate, with improved solvent (craze) resistance, achieved the ballistic performance of polycarbonate.

Novel electro-mechanical composites have been made with highly anisotropic electrical properties using interdiffusion between layers under controlled thermal conditions. The elastomeric nature of these systems has been used to develop sensitive sensors that function under large reversible deformation.

#### 5. Technology Transfer

Four companies, Kimberly-Clark, American National Can, International Paper and Dow Chemical are utilizing the microlayer technology developed under this ARO program to create new products.

Also, under this contract, composites have been made for the Army Research Laboratory, at Chestnut Run. Structure-property relationships have been established for these systems.